IN THE CLAIMS:

Please amend the claims to have the status and content indicated in the following listing of claims, wherein any cancellation of claims is made without prejudice.

- 12. (currently amended) A process for the preparation of a cell culture support comprising a microcarrier bead coated with a gelatine-like protein, the process comprising the step of coating a microcarrier bead with a gelatine-like protein, said gelatine-like protein having a molecular weight of from about 40 kDa to about 200 kDa, wherein at least 95% of the amino acid residues of the gelatine-like protein consist of Gly-Xaa-Yaa triplets, and wherein the gelatine-like protein comprises at least 15% of proline residues and less than 5% of hydroxyproline residues, wherein 3-dimensional globular domains are absent from the gelatine-like protein and wherein more than 75% of the gelatine-like protein has a uniform molecular weight.
- (original) The process according to claim 12, wherein the microcarrier bead is a nonporous bead.
- 14. (original) The process according to claim 12, wherein the microcarrier bead is a porous bead
- 15. (previously presented) The process according to claim 12, wherein the gelatine-like protein has a molecular weight of more than 60 kDa.
- 16. (previously presented) The process according to claim 12, wherein the gelatine-like protein has a molecular weight of less than about 150 kDa.
- 17. (previously presented) The process according to claim 12, further comprising the step of immobilizing the gelatine-like protein on the microcarrier.
- 18. (currently amended) The process according to claim 12, wherein more than 75% of the gelatine-like protein has a uniform molecular weight optionally within 2% of a selected molecular weight.

19. (previously presented) The process according to claim 12, wherein the gelatine-like protein is recombinantly produced.

20. (cancelled)

21. (previously presented) The process according to claim 12, wherein the gelatine-like protein has a net positive charge at pH 7-7.5.

22. (cancelled)

- 23. (previously presented) The process according to claim 12 wherein the gelatine-like protein comprises a single polypeptide chain.
- 24. (previously presented) The process according to claim 12 wherein the gelatine-like protein is essentially free of hydroxyproline residues.
- 25. (previously presented) The process according to claim 12 wherein the microcarrier beads comprise a material selected from the group consisting of modified dextran, cross-linked cellulose, porous polystyrene, diethylaminoethyldextran, chemically modified polysaccharides and unmodified polysaccharides and optionally at least 90% of the beads have a size in the range of from 50 μm to 500 μm.
- 26. (previously presented) The process according to claim 12 wherein the process is employed for producing microcarrier beads coated with the gelatine-like protein in bioreactors optionally with a loading of microcarrier beads in the bioreactor of from about 20 g/l to 40 g/l.
- 27. (currently amended) The process according to claim 19 wherein the gelatine-like protein comprises a single polypeptide chain and more than 75% of the gelatine like protein has a the uniform molecular weight is within 2% of a selected molecular weight, the selected molecular weight being more than 60 kDa and less than about 150 kDa.

28-29. (cancelled)

30. (new) The process according to claim 18 wherein the gelatine-like protein comprises a uniform molecular weight proportion selected from the group consisting of more than 85%, more than 95% and at least 98%.